

- 22 -

CLAIMS

1. An azetidinium-functional polyester.
5
2. A method of treating a substrate which comprises the step of contacting the substrate with a polyester according to claim 1.
- 10 3. A method according to claim 2 wherein the substrate comprises a cellulosic or keratinaceous textile material.
- 15 4. A composition comprising an azetidinium functionalised polyester according to claim 1 and a substrate-compatible carrier.
- 20 5. A composition according to claim 4 wherein the carrier comprises one or more of water and one or more surfactants.
6. A method of preparing a polyester according to claim 1 which comprises the step of:
 - 25 a) reacting an amine-containing (di)acid or (di)ol with a suitable co-reactant, and,
 - b) treating the product of step (a) with an epihalohydrin.
- 30

- 23 -

7. A method according to claim 6 wherein the step (a) occurs in the presence of a suitable a catalyst selected from the group comprising sulphuric acid, *p*-toluenesulphonic acid and a hafnium(IV) compound.
5
8. A method according to claim 6 wherein the diacid is an amine.
9. A method according to claim 8 wherein the diacid is an
10 iminodiacarboxylic acid in which each carboxylic acid moiety has a carbon number of 2-4.
10. A method according to claim 6 in which the diol is a
15 polyalkylene glycol in which the repeat unit has a carbon number of 2-3.